

PUBLICATION NUMBER : 07330945
PUBLICATION DATE : 19-12-95

APPLICATION DATE : 06-06-94
APPLICATION NUMBER : 06123962

APPLICANT : ASAHI CHEM IND CO LTD;

INVENTOR : IIJIMA HIDEKI;

INT.CL. : C08J 9/28 C08J 9/28 B01D 39/18 B01D 71/10 C12M 1/00

TITLE : PRODUCTION OF POROUS CELLULOSE FILM

ABSTRACT : PURPOSE: To produce efficiently a porous cellulose film which has a pore structure having a relatively small pore diameter and extremely uniform in the direction of film thickness and which is excellent in filtering and separating properties.

CONSTITUTION: A cuprammonium solution containing cellulose having an average mol.wt. of at least 5×10^4 is mixed with acetone and water to obtain an aqueous cellulose solution having a cellulose concentration of 2-4wt.%, an ammonia concentration of 1.6-3.2-wt.%, and an acetone concentration of 15-25wt.%. This solution is caused to undergo microphase separation at a temp. not lower than 35°C but not higher than the b.p. of acetone to produce a porous cellulose film preferably having an average pore diameter of 100-200nm.

COPYRIGHT: (C) JPO